



Sanbao town ■ Tongshan ■ Xuzhou ■ China
 Tel: +86(516)66631885 ■ Fax: +86 (516)83401885
 E-mail:plywood@cuzicn.com ■ www.plywoodsupplier.cn

Marine Plywood: Product Strength Data

All Bending and Elasticity data are expressed in N/mm²
 Density is Kilograms per 2500mm x 1250mm sheet.

Truth Marine Plywood					
Thickness	Bending Lengthways	Bending Crossways	Elasticity Lengthways	Elasticity Crossways	Density per sheet (kg)
4mm	44	24	6000	1500	6-7
5mm	40	26	5800	2000	9-10
6mm	48	36	6000	3300	12-13
9mm	40	28	5000	4000	13-14
12mm	40	40	5000	4500	17-18
15mm	36	36	4500	3500	24-25
18mm	36	36	4500	3500	27-28
25mm	40	40	4000	4000	40-41

Truth Elite Plus Marine Plywood					
Thickness	Bending Lengthway	Bending Crossways	Elasticity Lengthways	Elasticity Crossways	Density per sheet (kg)
4mm	110	45	10500	5000	8-9
6mm	100	50	9500	5500	14-15
9mm	80	50	7400	5500	21-22
12mm	75	60	6800	5000	30-31
15mm	72	60	7000	5000	34-35
18mm	65	59	6800	4800	42-43
25mm	61	55	6600	4650	58-60

Whilst every effort is made to ensure the accuracy of data and advice given, it is only intended for general information. Truth wood co Ltd accepts no liability for loss or damage arising from use of the information supplied. All goods are sold subject to our Terms & Conditions.